DECOFIT[®] P



Technische Eigenschaften

Basis	Synthetic dispersion
Consistency	Paste
Curing system	Physical drying
Open time (*)	Approximately 15 to 20 Minuten
Drying time (*)	Approximately 24 hours
Density (DIN 53479)	Approximately 1,60 g/ml
Temperature resistance	-20°C tot +70°C (after hardening)
Consumption	250 – 650 g/m2

(*) These values can variate according to ambitient conditions such as temperature, humidity, substrate

Product description

DECOFIT® P is a ready to use adhesive for bonding decorative panels onto surfaces indoor.



www.nmc.eu

NMC sa Gert-Noël-Strasse – B-4731 Eynatten (+32 87 85 85 00 − +32 87 85 85 11 info@nmc.eu



DECOFIT[®] P



Properties

- Ready to use
- Strong adhesive power
- Solvent free
- Suitable for sanding
- Suitable for painting

Applications

Bonding of decorative mouldings, ceiling tiles and centres.

Packaging

- Colour: White
- Packaging size: Tube 400 gr
 - Cartridge 310ml Bucket 1-4-5-7 kg

Shelf life

At least 18 months in unopened packaging in a cool and dry storage place at temperatures between $+5^{\circ}$ C and $+25^{\circ}$ C.

Substrate

Nature: All usual porous building materials such as brick, concrete, plaster, wood.

Condition: clean, dry and free from dust and grease.

Pre-treatment: A primer is recommended for very porous substrates. We recommend a preliminary compatibility test.

DECOFIT[®] P



Application method

Method:

For wall insulation: Apply the adhesive on the wall, using a toothed 2,50mm spatula. Apply the undercoat to the wall and press down gently. Use a wallpaper paste knife or brush to ensure good adhesion.

For ceiling tiles and panelling: Apply 5 to 9 knobs of adhesive on the back of the tile or on the edge of the panneling. Place the tile on the ceiling by pressing gently.

Application temperature: +5°C to 35°C

Clean: Uncured Decofit® P may be removed from tools and materials with water. Cured adhesive must be removed mechanically.

Repair: with DECOFIT®P

Health,- and Safety recommendations

Take the usual labour hygiene into account. Consult the packaging label for more information.

NMC sa reserves the right to update the product line or its technical features to the state-of-the-art technology anytime and without previous announcement. All given information is to the best of our knowledge. If you have any questions concerning technical details please contact the NMC sa information service. Any partial reproduction or reprint shall require our explicit approval.

This data sheet has been prepared in accordance with the current state of our knowledge. We reserve the right to make modifications without prior notice. Without a written agreement to the contrary, our studies, descriptions, notices, advice or other technical documents concerning the functionality, behaviour or performance of goods are supplied as an indication only according to the common use of the goods under normal conditions of application, use and climate (moderate European regions), or those indicated to us by customers in writing. Save for the existence of fraud or gross negligence on our part, these studies, recommendations and other technical documents do not engage our liability. It is the customer's responsibility to check that they are suitable for the intended use.



